



AFNOR STANDARD T 36.005 Family I – Class 1b

FIXATEUR MINERAL is a mineral primer based on silicate potassium used to protect façade.

Main qualities :

- Excellent application on alkaline surfaces.
- Fixes and consolidates mineral surfaces.
- Remarkable surface penetration.
- Colourless after drying.



- Highly permeable to water vapour.
- Excellent adhesion.
- Easy to coat.
- NF Environment certification in process.

Technical characteristic data

<p>Composition :</p> <ul style="list-style-type: none"> • Binder : potassium silicate <p>Mass density at 20°C : 1,14 gr/cm³ +/- 0,05</p> <p>Non volatile matter in weight : 22,5% +/- 2%</p> <p>Non volatile matter in volume : 11% +/- 2%</p>	<p>Drying (20°C – 65% relative humidity) :</p> <ul style="list-style-type: none"> • Re-coat : 24 hours <p>Average spreading rate : may vary according to surface</p> <p>Aspect in drum : fluid</p> <p>Aspect when dry : mat satin</p> <p>Gloss : < 1% at 85°.</p>
--	---

Destination :

FIXATEUR MINERAL is used to saturate friable mineral surfaces before overcoating with **ROCOSIL**. Never apply it on organic substrates. For interior, **FIXATEUR MINERAL** may be applied on plaster.

Surface preparation :

Surfaces must be clean, dry and prepared in conformity with the general conditions of use pursuant to the technical regulations of use (DTU) and standardization currently in force. Clean the surfaces by the appropriated mechanical or chemical means in order to obtain a dry, sound surface. Remove any potential micro-organisms with **ONIP MOUSSE** or **FONGIVORE**.

Apply by brush or roller :

- Friable surfaces : Prime with **FIXATEUR MINERAL** pure or dilute with 15% water.
- Sound surfaces : Use **FIXATEUR MINERAL** to dilute the 1st coat of **ROCOSIL** at 50%.

Precautions of use :

Do not apply on damp, greasy or frozen surfaces.

	Exterior	Interior
Ambient air temperature	minimum + 5°C	> 8°C
Temperature of surface ready to paint	minimum + 5°C / maximum + 35°C	
Humidity of surface ready to paint	< 5%	< 5%
Relative hygrometry	< 80%	< 65%

Use :

Apply **FIXATEUR MINERAL** in 1 coat by :

- Brush : Silkor aqua type.
- Roller : short hair piles (10mm).
- Tools cleaning : water.

Pack size : 15 L

Colours :

- Colourless opalescent.



Storage in hermetical original pack : 24 months keep away from heat and gel.

Hygiene and security (directive 2008/54/CE – 30th adaptation) :

Refer to security data sheet in force on : <http://www.onip.com>

Maximum content of VOC in the product ready to use (directive 2004/42/CE) : 10g/l

Version : 02/2010

Note : This notice aims informing our customers on the properties of our product. Information data as shown are based on our current knowledge and the tests results from the conditions of use complying with standards and the technical regulations of use (DTU) in force. Due to permanent technical evolution, our customers - before any implementation - have to check with our departments that this notice has not been replaced by an updated version. This data sheet cancels and replaces all previous versions. In case of complaint, only this document shall be evidence.

PEINTURES ONIP

Export Department : LES PEINTURES SAFE – 38 rue Richard Vian – 91530 SAINT CHERON - FRANCE

Tel : 33 (0) 1 69 14 15 30 – Fax : 33 (0) 1 69 14 15 35 + 33 (0) 64 56 57 61 - Email salle@onip.com

Commercial & administrative departments : 125-127, avenue de Fontainebleau - 94276 LE KREMLIN-BICETRE Cedex - FRANCE

Tel : 33 (0) 1 46 72 30 95 – Fax : 33 (0) 1 46 72 36 65 - Email administratif@onip.com

Central warehouse and laboratory - Usine du Val de l'Iton - 27400 HONDOUVILLE - FRANCE

Tel : 33 (0) 2 32 50 90 16 – Fax : 33 (0) 2 32 50 90 20 - Email labo@onip.com

Production units are certified ISO 9001/2000