



AFNOR STANDARD T 36.005 - Family I - Class 7b2

**LABEL'ONIP MAT** is the first lacquer paint with good flow certified with the European Ecolabel.

**LABEL'ONIP MAT** is the new generation of water-based lacquer paint combining the resistance of alkyd and the odourless performance of acrylic.

### Main qualities :

- Easy to coat.
- Very low odour.
- Excellent whiteness and hiding power.



- Fast drying
- Certified European Ecolabel Licence N°FR/05/04.
- Good adhesion on surfaces painted with alkyd paints.
- Suitable for use on alkaline surfaces.

### Technical characteristic data

Composition in white : • Binder : Modified acrylic dispersion • Solid constituent : Titanium dioxide + mineral extenders Mass density at 20°C : 1,52 gr/cm <sup>3</sup> +/- 0,05 Non volatile matter in weight : 66% +/- 2% Non volatile matter in volume : 42% +/- 2%	Aspect in drum : consistent Drying (20°C - 65% relative humidity) : • Dry to the touch : 1 hour • Re-coat : 12 hours Average spreading rate : 9 to 10m <sup>2</sup> /L Aspect : flat matt finish Gloss : < 4% @ 85°
---	---

**Destination :** LABEL'ONIP MAT is used for interior on most types of internal coverings and masonry. It gives a "lacquer-like" quality finishing on walls and ceilings in new as well as in maintenance works.

**Surface preparation :** Surfaces must be clean, dry and prepared in conformity with the general conditions of use pursuant to the technical regulations of use (DTU) and standardization currently in force. Clean the surfaces by the appropriated mechanical or chemical means in order to obtain a dry, sound and clean surface. Remove all micro-organisms by using **ONIP MOUSSE** or **FONGIVORE**.

In case of problematic surfaces, prime them with the adapted Onip primers :

- Friable surface : **DURFIX'ONIP** or **ONIPRIM** diluted 20% white spirit.
- Porous, non absorbing surfaces and old adhesive paints : **ONIPRIM** (diluted 10% white-spirit).
- Ferrous metals : **ROSTOSAM** (diluted 5% white-spirit).
- Non ferrous metals : **OLPRIMALO**
- New plaster, plasterboard, fillers and to obtain a lacquer finishing : **LABEL'ONIP IMPRESSION**.

**Precautions of use :** Do not apply on moisture, greasy or frozen surfaces. Old paints have to be sand papered.

	Interior
Ambient air temperature	> 8°C
Humidity of surface ready to paint	< 5%
Relative hygrometry	< 65%

### Use :

Apply **LABEL'ONIP MAT** pure in 1 or 2 coats :

- Brush (type Silkor Aqua).
- Roller (short pile sleeve 5 mm to obtain a flat finish) (short pile sleeve 10 mm for eggshell finish).
- Airless gun (nozzle 17 to 21/1000") (possible dilution 5% water). Surfaces should be primed with **LABEL'ONIP IMPRESSION**.
- Tools cleaning : water.

**Pack size :** White (1L - 4L - 15L) Bases PO2, PO3, POY (1L - 4L)

**Colours :** White

Over 2000 colours from COLOR'ONIP colour cards. + bases PO2, PO3, POY



**Storage in hermetical original pack :** 24 months keep away from heat and gel.

**Hygiene and security (directive 2008/54/CE - 30<sup>th</sup> adaptation) :**

Refer to security data sheet in force on : <http://www.onip.com>

Maximum content of VOC in the product ready to use (directive 2004/42/CE) : 15g/L.

**Version :** 08/2009

**Note :** This notice aims informing our customers on the properties of our product. Information data as shown are based on our current knowledge and the tests results from the conditions of use complying with standards and the technical regulations of use (DTU) in force. Due to permanent technical evolution, our customers - before any implementation - have to check with our departments that this notice has not been replaced by an updated version. This data sheet cancels and replaces all previous versions. In case of complaint, only this document shall be evidence.

## PEINTURES ONIP

Export Department : LES PEINTURES SAFE - 38 rue Richard Vian - 91530 SAINT CHERON - FRANCE

Tel : 33 (0) 1 69 14 15 30 - Fax : 33 (0) 1 69 14 15 35 + 33 (0) 64 56 57 61 - Email [salle@onip.com](mailto:salle@onip.com)

Commercial & administrative departments : 125-127, avenue de Fontainebleau - 94276 LE KREMLIN-BICETRE Cedex - FRANCE

Tel : 33 (0) 1 46 72 30 95 - Fax : 33 (0) 1 46 72 36 65 - Email [administratif@onip.com](mailto:administratif@onip.com)

Central warehouse and laboratory - Usine du Val de l'Iton - 27400 HONDOUVILLE - FRANCE

Tel : 33 (0) 2 32 50 90 16 - Fax : 33 (0) 2 32 50 90 20 - Email [labo@onip.com](mailto:labo@onip.com)

Production units are certified ISO 9001/2000