



AFNOR STANDARD T 36.005 - Family I – Class 7b2

OPACRYL IMPRIM is an acrylic primer used indoor and outdoor in most wall coverings such as : concrete, filler, cement, plasterboards, plaster, fat filler, acrylic filler and sound paints.

Main qualities :

- Easy to coat
- Interior over-coating by acrylic and alkyd paints.
- Good resistance to surface alkalinity.
- Good masking power.
- Fast drying.
- Complies with NF environmental rules (certificate N° 27/03)

Technical characteristic data

Composition in white :

- Binder : styrene acrylic dispersion
 - Solid constituent : titanium dioxide + fillers
- Mass density at 20°C : 1,52 gr/cm³ +/- 0,05
 Non volatile matter in weight : 63% +/- 2%
 Non volatile matter in volume : 44% +/- 2%

Drying (20°C – 65% relative humidity) :

- Dry to the touch : 2 hours
 - Re-coat : 12 hours
- Average spreading rate : 9 m²/L
 Aspect in drum : unctuous
 Aspect when dry : mat

Destination :

OPACRYL IMPRIM in an acrylic primer used indoor and outdoor on sound surfaces. Indoor and outdoor use on every traditional surfaces of buildings.

Surface preparation :

Surfaces must be clean, dry and prepared in conformity with the general conditions of use pursuant to the technical regulations of use (DTU) and standardization currently in force. Clean the surfaces by the appropriated mechanical or chemical means in order to obtain a dry, sound and clean surface. Treat micro-organisms with **FONGIVORE** or **ONIP MOUSSE**.

Precautions of use :

Do not apply on moisture, greasy or frozen surfaces. Remove all micro-organisms.

	interior
Ambient air temperature	> 8°C
Temperature of surface ready to paint	> 8°C
Humidity of surface ready to paint	< 5%
Relative hygrometry	< 65%

Use :

Apply **OPACRYL IMPRIM** in 1 coat :

- Brush (silkor aqua) : pure.
- Short hair roller (14mm) : pure.
- Airless gun (nozzle 21 to 26/1000") : dilution 3 to 5% water.
- On absorbing surface : dilution 5% water.
- Tools cleaning : water.

Pack size : 4 L - 15 L

Colours :

- White.
- From white, over 1200 colours are available via the Color'Onip Tinting System.



Storage in hermetical original pack : 24 months keep away from heat and gel.

Hygiene & safety (directive 2008 /58/ CE – 30th adaptation) : refer to security data sheet in use.

Maximum content of VOC in the product ready to use (directive 2004/42/CE) : 20g/L.

Version : 02/2010

Note : This notice aims informing our customers on the properties of our product. Information data as shown are based on our current knowledge and the tests results from the conditions of use complying with standards and the technical regulations of use (DTU) in force. Due to permanent technical evolution, our customers - before any implementation - have to check with our departments that this notice has not been replaced by an updated version. This data sheet cancels and replaces all previous versions. In case of complaint, only this document shall be evidence.

PEINTURES ONIP

Export Department : LES PEINTURES SAFE – 38 rue Richard Vian – 91530 SAINT CHERON - FRANCE

Tel : 33 (0) 1 69 14 15 30 – Fax : 33 (0) 1 69 14 15 35 + 33 (0) 64 56 57 61 - Email salle@onip.com

Commercial & administrative departments : 125-127, avenue de Fontainebleau - 94276 LE KREMLIN-BICETRE Cedex - FRANCE

Tel : 33 (0) 1 46 72 30 95 – Fax : 33 (0) 1 46 72 36 65 - Email administratif@onip.com

Central warehouse and laboratory - Usine du Val de l'Iton - 27400 HONDOUVILLE - FRANCE

Tel : 33 (0) 2 32 50 90 16 – Fax : 33 (0) 2 32 50 90 20 - Email labo@onip.com

Production units are certified ISO 9001/2000