



**AFNOR STANDARD** T 36.005 - Family I - Class 7b2/2b

**PURvelours d'Onip** is an interior velvet paint forming a resistant film paint when dry. Its alkyd urethane resin provides remarkable scratches and abrasion resistance.

**Main qualities :**

- Easy to coat.
- Excellent paint film resistance.
- Velvet finishing.
- Washable.
- Water resistant.



- Good opacity and whiteness.
- Low odour.
- Good open time.
- Good body power.
- Complies with Ecolabel rules (certificate N° 05/19B)

### Technical characteristic data

|   |   |
|---|---|
| <p>Composition in white :</p> <p>Binder : urethane alkyd + acrylic emulsion</p> <p>Solid constituent : titanium dioxide + fillers</p> <p>Mass density at 20°C : 1,32 gr/cm<sup>3</sup> +/- 0,05</p> <p>Non volatile matter in weight : 57,2% +/- 2%</p> <p>Non volatile matter in volume : 43,5% +/- 2%</p> | <p>Drying (20°C - 65% relative humidity) :</p> <ul style="list-style-type: none"> <li>• Dry to the touch : 2 hours</li> <li>• Re-coat : 12 hours</li> </ul> <p>Average spreading rate : 12 m<sup>2</sup>/L</p> <p>Aspect when dry : velvet</p> <p>Aspect in drum : unctuous</p> <p>Gloss : 8 - 12% at 60°</p> |
|---|---|

**Destination :** **PURvelours d'Onip** is used on most internal walls coverings when a perfect durable flat finishing is required.

**Surface preparation :** Surfaces must be clean, dry and prepared in conformity with the general conditions of use pursuant to the technical regulations of use (DTU) and standardization currently in force. Clean the surfaces by the appropriated mechanical or chemical means in order to obtain a dry, sound and clean surface, use the proper **ONIP** primers on friable or porous surfaces, metals, woods... :

- Friable surface : **DURFIX'ONIP.**
- Porous surfaces : **ONIPRIM.**
- Ferrous metals : **ROSTOSAM.**
- Non ferrous metals : **OLPRIMALO.**
- Plaster, plasterboard, fillers : **PRIMONIP HYDRO G** or **IMPRESSION STAR.**
- Interior woods : **PURvelours d'Onip** direct or pre-coat with **PRIMONIP HYDRO G.**

**Precautions of use :** Do not apply on moisture, greasy or frozen surfaces.

|                                    | <b>Interior</b> |
|------------------------------------|-----------------|
| Ambient air temperature            | > 8°C           |
| Humidity of surface ready to paint | < 5%            |
| Relative hygrometry                | < 65%           |

**Use :**

Apply **PURvelours d'Onip** pure in 1 or 2 coats :

- Brush and roller (4mm or 10mm hair length) : pure.
- Airless gun (nozzle 9 to 15/1000") : pure.
- Tools cleaning : water.

**Pack size :** white (1L - 4 L - 15 L) - PO2 + PO3 + POY base paints (1 L - 4 L)

**Colours :**

- White + PO2 + PO3 + POY
- Over 2000 colours are available via the Color'Onip Tinting System.



**Storage in hermetical original pack :** 24 months keep away from heat and gel.

**Hygiene & safety (directive 2008/58/CE 30<sup>th</sup> adaptation) :** refer to security data sheet in use.

Maximum content of VOC in the product ready to use (directive 2004/42/CE) : 15g/L.

**Version : 08/2009**

**Note :** This notice aims informing our customers on the properties of our product. Information data as shown are based on our current knowledge and the tests results from the conditions of use complying with standards and the technical regulations of use (DTU) in force. Due to permanent technical evolution, our customers - before any implementation - have to check with our departments that this notice has not been replaced by an updated version. This data sheet cancels and replaces all previous versions. In case of complaint, only this document shall be evidence.

### PEINTURES ONIP

**Export Department : LES PEINTURES SAFE - 38 rue Richard Vian - 91530 SAINT CHERON - FRANCE**

**Tel : 33 (0) 1 69 14 15 30 - Fax : 33 (0) 1 69 14 15 35 + 33 (0) 64 56 57 61 - Email [salle@onip.com](mailto:salle@onip.com)**

Commercial & administrative departments : 125-127, avenue de Fontainebleau - 94276 LE KREMLIN-BICETRE Cedex - FRANCE

Tel : 33 (0) 1 46 72 30 95 - Fax : 33 (0) 1 46 72 36 65 - Email [administratif@onip.com](mailto:administratif@onip.com)

Central warehouse and laboratory - Usine du Val de l'Iton - 27400 HONDOUVILLE - FRANCE

Tel : 33 (0) 2 32 50 90 16 - Fax : 33 (0) 2 32 50 90 20 - Email [labo@onip.com](mailto:labo@onip.com)

**Production units are certified ISO 9001/2000**