



NF T 36.005 - Family I - Class 7b2  
 XP P 84403 I1 to I4  
 EN 1062-1 G3-E3-V1-W2-A2 to A5

**AFNOR STANDARD**

**SOUPLONIP FINITION LISSE 9003** is the smooth waterproof top coat of **SOUPLONIP 9003** systems for façade. Conform with French DTU 42.1.

**Main qualities :**

- Highly flexible even at low temperature (-10°C).
- Breathable and permeable to vapour water.
- Showerproof.



- Mat velvet finishing.
- Easy to coat.
- European Ecolabel in process

### Technical characteristic data

Composition in white :	Aspect in drum	: thick
Binder	Drying (20°C - 65% relative humidity) :	
Solid constituent	• Dry to the touch	: 4 to 5 hours (according to exposure)
	• Re-coat	: 24 hours
Mass density at 20°C	Average spreading rate	: 2 to 3,3 m <sup>2</sup> /kg per coat
Non volatile matter in weight		(according to waterproof system)
Non volatile matter in volume	Aspect	: mat
	Gloss	: < 1,5% @ 85°

**Destination :**

**SOUPLONIP FINITION LISSE 9003** is the smooth top coat of the **SOUPLONIP 9003** waterproofing system for facade.

**Surface preparation :**

Surfaces must be sound, dry and prepared in conformity with the general conditions of use pursuant to the technical regulations of use (DTU) and standardization currently in force. Clean the surfaces by the appropriated mechanical or chemical means in order to obtain a dry, sound and clean surface.

Remove any micro-organisms and algae with **ONIP MOUSSE** or **FONGIVORE**.

Overcoat **SOUPLONIP FINITION LISSE 9003** after priming the surface with **SOUPLONIP IMPRESSION 9003** or **SOUPLONIP BASE 9003** or **SOUPLONIP SOUS COUCHE RELIEF 9003**.

On some specific surfaces, prime with the adapted **ONIP** primers : **ONIPRIM**, **DURFIX'ONIP**, **OLPRIMALO**.

In these cases, **SOUPLONIP FINITION LISSE 9003** will be coated in thicker coat (refer to our technical service).

**Precautions of use :** Do not apply on damp, condensing, greasy or frozen surfaces.

	Exterior
Ambient air temperature	> 5°C
Surface temperature	minimum + 5°C / maximum + 35°C
Humidity of surface ready to paint	< 5%
Relative hygrometry	< 80%

**Use :**

**SOUPLONIP FINITION LISSE 9003** has to be coated pure :

- By brush (Silkor aqua).
- By long pile sleeve polyamide roller (14mm).
- Tools cleaning and dilution : water.

**Pack size :** White (15L) Bases PO2, PO3

**Colours :** White

Over 1800 colours from **COLOR'ONIP** colour cards + bases PO2, PO3



**Storage in hermetical original pack :** 24 months keep away from heat and gel.

**Hygiene and security (directive 2008/58/CE - 30<sup>th</sup> adaptation) :**

Refer to security data sheet in force on : <http://www.onip.com>

Maximum content of VOC in the product ready to use (directive 2004/42/CE) : 20g/L.

**Storage in hermetical original pack :** 24 months keep away from heat and gel.

**Version :** 02/2010

**Note :** This notice aims informing our customers on the properties of our product. Information data as shown are based on our current knowledge and the tests results from the conditions of use complying with standards and the technical regulations of use (DTU) in force. Due to permanent technical evolution, our customers - before any implementation - have to check with our departments that this notice has not been replaced by an updated version. This data sheet cancels and replaces all previous versions. In case of complaint, only this document shall be evidence.

### PEINTURES ONIP

Export Department : LES PEINTURES SAFE - 38 rue Richard Vian - 91530 SAINT CHERON - FRANCE

Tel : 33 (0) 1 69 14 15 30 - Fax : 33 (0) 1 69 14 15 35 + 33 (0) 64 56 57 61 - Email [salle@onip.com](mailto:salle@onip.com)

Commercial & administrative departments : 125-127, avenue de Fontainebleau - 94276 LE KREMLIN-BICETRE Cedex - FRANCE

Tel : 33 (0) 1 46 72 30 95 - Fax : 33 (0) 1 46 72 36 65 - Email [administratif@onip.com](mailto:administratif@onip.com)

Central warehouse and laboratory - Usine du Val de l'Iton - 27400 HONDOUVILLE - FRANCE

Tel : 33 (0) 2 32 50 90 16 - Fax : 33 (0) 2 32 50 90 20 - Email [labo@onip.com](mailto:labo@onip.com)

Production units are certified ISO 9001/2000