



## PRODUCT DATA SHEET

# PRIMAIRE POLYFOND AQUA

PR0861/022009/UK

AFNOR class : ONU 1263 AFNOR T 36005 - Family I, class 7b2-4a  
Custom code N° 3209 90 00

EEC maximum content of VOC of the product (cat. A/j): 140g/L (2010).  
Maximum content of VOC in the product ready to use: 20g/L

### PRIMAIRE POLYFOND AQUA

Acrylic copolymer modified urethane alkyd water based primer for interior & exterior.

Suitable on :

- ferrous metals (iron, galvanized & electro-zinc sheets)
- non ferrous metals (copper, aluminium, brass)
- alkaline surfaces (fiber cement, cement filler, concrete, bricks)
- mineral surfaces (stones, glass)
- plastics (PVC, for others consult our technical services)
- isolating primer on sound paints and pre-lacked sheets steel

### PERFORMANCES

- excellent adhesion
- applicable on damp surfaces
- easy to use
- tools cleaning and dilution with water

### CHARACTERISTICS

At 20°C & 65% relative humidity

<i>ASPECT</i>	:	Satin	
<i>COLOURS</i>	:	white + colours on demand	
<i>VISCOSITY</i>	:	1680 mPa.s by Contrave mobile 3	
<i>MASS DENSITY</i>	:	1,33 +/- 0.02 g/cm <sup>3</sup>	
<i>DRY EXTRACT</i>	:	in weight : 56% +/- 1%	
		in volume : 36% +/- 1%	
<i>DRYING</i>	:	dust dry	15 to 20 min.
		touch dry	45min.
		handling	2h.
		re-coat	after 2h.
		(beyond 48h a sand papering is required)	

### INSTRUCTIONS OF USE

At 20°C & 65% relative humidity

#### PRECAUTIONS OF USE :

Apply on sound surfaces prepared in conformity with DTU in force.

#### COATING & PREPARATION : apply in 1 coat

Brush – roller – airless gun (possible dilution)	2 to 5% <b>water</b>
Pneumatic gun	5 to 10% <b>water</b>
Tools cleaning	<b>water</b>

**THEORETICAL COVERAGE** : at 40μ dry, **8 m<sup>2</sup>/ L**

**PACK SIZE** : 1 L – 4 L - 15 L

**STORAGE** : 12 months in original drum. Keep away from frost & heat.

This notice aims informing our customers on the properties of our product, and the tests results from the conditions of use complying with standards and the technical regulations of use in force. Due to permanent technical developments, our customers - prior to any implementation - have to check with our departments that this notice has not been replaced by an updated version.

Information data as shown are based on our current knowledge This data sheet cancels and replaces all previous versions. In case of complaint, this document shall be the only document applicable.

### VERNIS PICARD

125-127 avenue de Fontainebleau - 94276 LE KREMLIN-BICETRE - Cedex - FRANCE  
Téléphone : (33) 1 45 15 08 08      Télécopie : (33) 01 46 71 45 72      Web site : vernis-picard.com