



AFNOR STANDARD T 36.005 - Family I - Class 7b2

BRILLACRYL SATIN is an interior satin paint recommended for hospitals, kitchens, refectories, offices and commercial shops. In exterior it is applied on façade, woods...

Main qualities :

- Easy to coat.
- Odourless.
- Excellent opacity.
- Easy maintenance, washable.
- Alkali resisting.
- Non-saponifying.
- Fast drying.
- Complies with NF environmental rules (certificate N° 27/22)

Technical characteristic data

Composition in white :

Binder	: styrene acrylic dispersion
Solid constituent	: titanium dioxide + fillers
Mass density at 20°C	: 1,44 gr/cm ³ +/- 0,05
Non volatile matter in weight	: 63% +/- 2%
Non volatile matter in volume	: 44% +/- 2%

Drying (20°C - 65% relative humidity) :

• Dry to the touch	: 6 hours
• Re-coat	: 24 hours
Average spreading rate	: 11m ² /L
Aspect when dry	: satin
Aspect in drum	: consistent
Gloss	: 15 - 20% at 60°

Destination : BRILLACRYL SATIN is a quality satin finishing paints for walls in new as well as in maintenance works.

Surface preparation : Surfaces must be clean, dry and prepared in conformity with the general conditions of use pursuant to the technical regulations of use (DTU) and standardization currently in force. Clean the surfaces by the appropriated mechanical or chemical means in order to obtain a dry, sound and clean surface.

Remove all micro-organisms with **ONIP MOUSSE** or **FONGIVORE**.

Use the proper ONIP primers on friable or porous surfaces, metals, woods... :

- Friable surface : **DURFIX'ONIP**.
- Old flouing paints & porous surfaces : **ONIPRIM** or **PRIMONIP HYDRO G**
- Ferrous metals : **ROSTOSAM**.
- Non ferrous metals : **OLPRIMALO**.
- Woods : **MICRONIP SB**
- Not too absorbing surfaces : pure

Precautions of use : Do not apply on moisture, greasy or frozen surfaces.

	Exterior	Interior
Ambient air temperature	> 5°C	> 8°C
Humidity of surface ready to paint	< 5%	< 5%
Relative hygrometry	< 80%	< 65%

Use :

Apply **BRILLACRYL SATIN** in 2 coats preferably on primed surfaces :

- Brush and roller (10mm hair length) : pure.
- Airless gun (nozzle 18 to 21/1000") : dilution 3 to 5% water.
- Tools cleaning : water.

Pack size : white + PO2 + PO3 + PY bases (1L - 4L - 15 L).

Colours :

- White + 2000 colours are available via the Color'Onip Tinting System.



Storage in hermetical original pack : 24 months keep away from heat and gel.

Hygiene & safety (directive 2008 / 58 / CE - 30th adaptation) : refer to security data sheet in use.

Maximum content of VOC in the product ready to use (directive 2004/42/CE) : 30g/L.

Version : 08/2009

Note : This notice aims informing our customers on the properties of our product. Information data as shown are based on our current knowledge and the tests results from the conditions of use complying with standards and the technical regulations of use (DTU) in force. Due to permanent technical evolution, our customers - before any implementation - have to check with our departments that this notice has not been replaced by an updated version. This data sheet cancels and replaces all previous versions. In case of complaint, only this document shall be evidence.

PEINTURES ONIP

Export Department : LES PEINTURES SAFE - 38 rue Richard Vian - 91530 SAINT CHERON - FRANCE

Tel : 33 (0) 1 69 14 15 30 - Fax : 33 (0) 1 69 14 15 35 + 33 (0) 64 56 57 61 - Email salle@onip.com

Commercial & administrative departments : 125-127, avenue de Fontainebleau - 94276 LE KREMLIN-BICETRE Cedex - FRANCE

Tel : 33 (0) 1 46 72 30 95 - Fax : 33 (0) 1 46 72 36 65 - Email administratif@onip.com

Central warehouse and laboratory - Usine du Val de l'Iton - 27400 HONDOUVILLE - FRANCE

Tel : 33 (0) 2 32 50 90 16 - Fax : 33 (0) 2 32 50 90 20 - Email labo@onip.com

Production units are certified ISO 9001/2000