



AFNOR STANDARD T 36.005 Family I – Class 7b2
 XP P 84403 D3
 EN 1062-1 G3 E3 V2 W2 A0

FLEXONIP FINITION is a semi thick, acrylic paint for façade protection and decoration.

Main qualities :

- Microporous.
- Easy to coat.
- Good hiding and body power.
- Deep matt.



- NF Environnement certificate in process.
- Good vapour water permeability / NFT30704 norm
- Good resistance to dirtying and weathering.
- Anti-cryptogamic treated.

Technical characteristic data

Composition in white :		Aspect in drum	: unctuous
Binder	: acrylic resin	Drying (20°C – 65% relative humidity) :	
Solid constituent	: titanium dioxide + mineral extenders	• Dry to the touch	: 6 hours
Mass density at 20°C	: 1,42 gr/cm ³ +/- 0,05	• Re-coat	: 24 hours
Non volatile matter in weight	: 64% +/- 2%	Average spreading rate	: 2,8 to 3,5 m ² /L per coat.
Non volatile matter in volume	: 49% +/- 2%	Aspect	: matt
		Gloss	: < 1,5% @ 85°

Destination :

FLEXONIP FINITION is applied after priming on sound exterior surfaces in new as well as in renovation works (concrete, cement filler...).

Surface preparation :

Surfaces must be clean, dry and prepared in conformity with the general conditions of use pursuant to the technical regulations of use (DTU) and standardization currently in force. Clean the surfaces by the appropriated mechanical or chemical means in order to obtain a dry, sound and clean surface. Remove all micro-organisms by using **ONIP MOUSSE** or **FONGIVORE**. Refer to our book of façade to choose the appropriated primer.

Precautions of use : Ensure the substrate is dry, free from grease and other contaminants.

	Exterior
Ambient air temperature	minimum + 5°C
Temperature of surface ready to paint	minimum + 5°C / maximum + 35°C
Humidity of surface ready to paint	< 5%
Relative hygrometry	< 80%

Use :

Apply **FLEXONIP FINITION** with a polyamide roller (long pile sleeve 20 mm) or with an acrylic brush (silkor aqua type).

- On **ONIPRIM** or **DURFIX ONIP** at 500 gr./m².
- On **FLEXONIP IMPRESSION** at 400 gr./m².
- Tools cleaning : water.

Pack size : 15L

Colours : White + PO2 base
 Over 1700 colours from COLOR'ONIP colour cards

Storage in hermetical original pack : 24 months keep away from heat and gel.

Hygiene & safety (directive 2008/58/CE – 30th adaptation) : refer to security data sheet in use.

Maximum content of VOC in the product ready to use (directive 2004/42/CE) : 25g/L.

Version : 02/2010

Note : This notice aims informing our customers on the properties of our product. Information data as shown are based on our current knowledge and the tests results from the conditions of use complying with standards and the technical regulations of use (DTU) in force. Due to permanent technical evolution, our customers - before any implementation - have to check with our departments that this notice has not been replaced by an updated version. This data sheet cancels and replaces all previous versions. In case of complaint, only this document shall be evidence.

PEINTURES ONIP

Export Department : LES PEINTURES SAFE – 38 rue Richard Vian – 91530 SAINT CHERON - FRANCE

Tel : 33 (0) 1 69 14 15 30 – Fax : 33 (0) 1 69 14 15 35 + 33 (0) 64 56 57 61 - Email salle@onip.com

Commercial & administrative departments : 125-127, avenue de Fontainebleau - 94276 LE KREMLIN-BICETRE Cedex - FRANCE

Tel : 33 (0) 1 46 72 30 95 – Fax : 33 (0) 1 46 72 36 65 - Email administratif@onip.com

Central warehouse and laboratory - Usine du Val de l'Iton - 27400 HONDOUVILLE - FRANCE

Tel : 33 (0) 2 32 50 90 16 – Fax : 33 (0) 2 32 50 90 20 - Email labo@onip.com

Production units are certified ISO 9001/2000