



AFNOR STANDARD T 36.005 - Family I - Class 7b2

L'EAUNIP BRILLANT is an acrylic microporous glossy lacquer paint for woods.

Main qualities :

- Easy to coat.
- Low odour, fast drying.
- Excellent whiteness and hiding power.
- Good microporosity on woods
- Alkali resistant.
- Good adhesion on alkyd surfaces.
- Levelling finish.
- Complies with NF environmental rules (certificate N° 27/18)

Technical characteristic data

Composition in white :	Aspect in drum	: consistent
Binder	Drying (20°C - 65% relative humidity) :	
Solid constituent	• Dry to the touch	: 4 hours
	• Re-coat	: 12 hours
Mass density at 20°C	Average spreading rate	: 12m ² /L
Non volatile matter in weight	Aspect	: gloss lacquer
Non volatile matter in volume	Gloss	: > 60% @ 20°

Destination :

L'EAUNIP BRILLANT is used pure or diluted with 3% water on woods in interior and exterior previously primed with **L'EAUNIP MAT**.

Surface preparation : Surfaces must be clean, dry and prepared in conformity with the general conditions of use pursuant to the technical regulations of use (DTU) and standardization currently in force. Clean the surfaces by the appropriated mechanical or chemical means in order to obtain a dry, sound and clean surface. Remove all micro-organism by using **ONIP MOUSSE** or **FONGIVORE**.

Precautions of use : Do not apply on moisture, greasy or frozen surfaces

	Exterior	Interior
Ambient air temperature	> + 5°C	> 8°C
Temperature of surface ready to paint	> + 5°C < + 35°C	
Humidity of surface ready to paint	< 5%	< 5%
Relative hygrometry	< 80%	< 65%

Use :

Apply **L'EAUNIP SATIN BRILLANT** in 2 coats :

- Brush (silkor aqua) : pure.
- Roller (short pile sleeve 5mm) : pure.
- Tools cleaning : water.

Pack size : White (4L - 15L)

Colours : White

Over 1200 colours from COLOR'ONIP colour cards



Storage in hermetical original pack : 24 months keep away from heat and gel.

Hygiene & safety (directive 2008/58/ CE - 30th adaptation) : refer to security data sheet in use.

Maximum content of VOC in the product ready to use (directive 2004/42/CE) : 100g/L.

Version : 08/2009

Note : This notice aims informing our customers on the properties of our product. Information data as shown are based on our current knowledge and the tests results from the conditions of use complying with standards and the technical regulations of use (DTU) in force. Due to permanent technical evolution, our customers - before any implementation - have to check with our departments that this notice has not been replaced by an updated version. This data sheet cancels and replaces all previous versions. In case of complaint, only this document shall be evidence.

PEINTURES ONIP

Export Department : LES PEINTURES SAFE - 38 rue Richard Vian - 91530 SAINT CHERON - FRANCE

Tel : 33 (0) 1 69 14 15 30 - Fax : 33 (0) 1 69 14 15 35 + 33 (0) 64 56 57 61 - Email salle@onip.com

Commercial & administrative departments : 125-127, avenue de Fontainebleau - 94276 LE KREMLIN-BICETRE Cedex - FRANCE

Tel : 33 (0) 1 46 72 30 95 - Fax : 33 (0) 1 46 72 36 65 - Email administratif@onip.com

Central warehouse and laboratory - Usine du Val de l'Iton - 27400 HONDOUVILLE - FRANCE

Tel : 33 (0) 2 32 50 90 16 - Fax : 33 (0) 2 32 50 90 20 - Email labo@onip.com

Production units are certified ISO 9001/2000