



NF T 36.005 - Family I – Class 7b2
 XP P 84403 I1 to I4
 EN 1062-1 G3-E5-S3 to S4-V2-W2-A2 to A5

AFNOR STANDARD

SOUPLONIP FINITION GRESEE 9003 is the textured "granite like" waterproof top coat of **SOUPLONIP 9003** systems for façade. Conform with French DTU 42.1.

Main qualities :

- Highly flexible even at low temperature (-10°C).
- Breathable and permeable to vapour water.
- Showerproof.



- Granite like finishing.
- Easy to coat.
- NF ENVIRONNEMENT certificate in process

Technical characteristic data

Composition in white : Binder : acrylic cross-linking dispersion Solid constituent : Titanium dioxide + mineral extenders. Mass density at 20°C : 1,75 gr/cm ³ +/- 0,05 Non volatile matter in weight : 82% +/- 2% Non volatile matter in volume : 47% +/- 2%	Aspect in drum : thick Drying (20°C – 65% relative humidity) : • Drying : 24 hours (according to exposure) Average spreading rate : 0,45 m ² /kg Aspect : mat
---	--

Destination :

SOUPLONIP FINITION TALOCHEE 9003 is the hawkgranite like top coat of the **SOUPLONIP 9003** waterproofing system for facade.

Surface preparation :

Surfaces must be sound, dry and prepared in conformity with the general conditions of use pursuant to the technical regulations of use (DTU) and standardization currently in force. Clean the surfaces by the appropriated mechanical or chemical means in order to obtain a dry, sound and clean surface.

Remove any micro-organisms and algae with **ONIP MOUSSE** or **FONGIVORE**.

Overcoat **SOUPLONIP FINITION GRESEE 9003** after priming the surface with **SOUPLONIP IMPRESSION 9003**, **ONIPRIM**, **DURFIX'ONIP**, **OLPRIMALO** for I1 waterproof system.

Overcoat **SOUPLONIP FINITION GRESEE 9003** after priming the surface with **SOUPLONIP BASE 9003** or **SOUPLONIP SOUS COUCHE RELIEF 9003** for I2 – I3 – I3C – I4 waterproof systems.
 (refer to our technical service).

Precautions of use : Do not apply on damp, condensing, greasy or frozen surfaces.

	Exterior
Ambient air temperature	> 5°C
Surface temperature	minimum + 5°C / maximum + 35°C
Humidity of surface ready to paint	< 5%
Relative hygrometry	< 80%

Use :

SOUPLONIP FINITION GRESEE 9003 has to be coated pure at 2.2 kg/m² :

With a plastic or stainless steel trowel.

For mechanical application use an equipment recommended for heavy pasty products.

Grit the product when it is still fresh, use a plastic trowel kept clean and damp.

The time of gritting may vary according to climate conditions.

Tools cleaning : water.

Pack size : White (15L)

Colours : White

200 colours from COLOR'ONIP FAÇADE colour card



Storage in hermetical original pack : 24 months keep away from heat and gel.

Hygiene and security (directive 2008/58/CE – 30th adaptation) :

Refer to security data sheet in force on : <http://www.onip.com>

Maximum content of VOC in the product ready to use (directive 2004/42/CE) : 25g/L.

Storage in hermetical original pack : 24 months keep away from heat and gel.

Version : 02/2010

Note : This notice aims informing our customers on the properties of our product. Information data as shown are based on our current knowledge and the tests results under the conditions of use complying with standards and the technical regulations of use (DTU) in force. Due to permanent technical evolution, our customers - before any implementation - have to check with our departments that this notice has not been replaced by an updated version. This data sheet cancels and replaces all previous versions. In case of complaint, only this document shall be evidence.

PEINTURES ONIP

Export Department : LES PEINTURES SAFE – 38 rue Richard Vian – 91530 SAINT CHERON - FRANCE

Tel : 33 (0) 1 69 14 15 30 – Fax : 33 (0) 1 69 14 15 35 + 33 (0) 64 56 57 61 - Email salle@onip.com

Commercial & administrative departments : 125-127, avenue de Fontainebleau - 94276 LE KREMLIN-BICETRE Cedex - FRANCE

Tel : 33 (0) 1 46 72 30 95 – Fax : 33 (0) 1 46 72 36 65 - Email administratif@onip.com

Central warehouse and laboratory - Usine du Val de l'Iton - 27400 HONDOUVILLE - FRANCE

Tel : 33 (0) 2 32 50 90 16 – Fax : 33 (0) 2 32 50 90 20 - Email labo@onip.com

Production units are certified ISO 9001/2000